

TEST REPORT

No.: XMIN2603000518CM06_EN

Issue Date: 2026-04-01

Page: 1 of 4

CUSTOMER NAME: RAMHOUSE, LLC
ADDRESS: RUSSIA, 115487, MOSCOW, NAGATINSKAYA ST., BUILDING 16,
HOUSING 1, CONSTRUCTION 5, ROOM 6H

Sample Name : MSPC Laminate Floor by Stone Floor
Product Specification : Thickness: 8.3+/- 1mm
Other Information : Product Description: Mineral Stone Polycomposite (MSPC)

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

Sample Source : Customer-delivered
Date of Receipt : 2026-03-20
Testing Period : 2026-03-20 ~ 2026-04-01
Test result(s) : For further details, please refer to the following page(s)
(Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co.,Ltd. Xiamen Branch

Bryan Hong

Authorized signatory



SGS-CSTC Standards Technical Services Co., Ltd.
Xiamen Branch Commercial General Laboratory

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.31 Xianghong Road, Xiang'An Torch Industrial Zone, Xiamen, Fujian Province, China 361101
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编: 361101

t (86-592) 5765857 www.sgs.com.cn
t (86-592) 5765857 sgs.china@sgs.com

Scan to see the report



XMIN2603000518CM06
Verification:
check.sgs.com.cn

TEST REPORT

No.: XMIN2603000518CM06_EN

Issue Date: 2026-04-01

Page: 2 of 4

Summary of Results:

No.	Test Item	Test Method	Result
1	Resistance To Staining	EN 438-2:2016+A1:2018 Section 26	See result

Original Sample Photo:



SGS-CSTC Standards Technical Services Co., Ltd.
Xiamen Branch Commercial General Laboratory

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China 361101
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编: 361101

t (86-592) 5765857 www.sgsgroup.com.cn
t (86-592) 5765857 sgs.china@sgs.com

TEST REPORT

No.: XMIN2603000518CM06_EN

Issue Date: 2026-04-01

Page: 3 of 4

1. Test Item: Resistance to Staining

Sample Description: See photo

Test Method: EN 438-2:2016+A1:2018 Section 26

Test Condition:

Step 1: Immerse a disc into the staining agent between 30 s and 60 s, quickly wipe off the edge of the disc once against the edge of the vessel. Place it on the test surface and immediately cover with an inverted glass Petri dish, keep it for specified time.

Step 2: Remove the glass Petri dish and lift off the disc. Soak up any remaining test liquid.

Step 3: Wash the test surface by lightly rubbing it with the wet cleaning cloth. Finally wipe the surface lightly with a dry cleaning cloth.

Step 4: Leave the test surface undisturbed for 30min without covering it.

Test Result:

Staining agent	Test condition	Test result
Acetone (AR)	Apply agent at ambient temperature, contact for 16h	Rating 5
Coffee (Nestlé®, 120g of coffee per liter of water)	Apply agent at approximately 80°C, contact for 16h	Rating 5
Sodium hydroxide (25% solution)	Apply agent at ambient temperature, contact for 10min	Rating 5
Hydrogen peroxide (30% solution)		Rating 5
Shoe polish (Red Bird®)		Rating 5



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd.
Xiamen Branch Commercial General Laboratory

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China 361101
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编: 361101

t (86-592) 5765857 www.sgsgroup.com.cn
t (86-592) 5765857 sgs.china@sgs.com

TEST REPORT

No.: XMIN2603000518CM06_EN

Issue Date: 2026-04-01

Page: 4 of 4

Note: According to EN 438-2:2016+A1:2018 Table 8, rating 5 is the best and rating 1 is the worst.

Numerical rating	Description
5	No change Test area indistinguishable from adjacent surrounding area
4	Minor change Test area distinguishable from adjacent surrounding area, only when the light source is mirrored on the test surface and is reflected towards the observer's eye, e. g. discoloration, change in gloss and colour
3	Moderate change Test area distinguishable from adjacent surrounding area, visible in several viewing directions, e. g. discoloration, change in gloss and colour
2	Significant change Test area clearly distinguishable from adjacent surrounding area, visible in all viewing directions, e. g. discoloration, change in gloss and colour, and / or structure of the surface slightly changed, e.g. cracking, blistering
1	Strong change The structure of the surface being distinctly changed and / or discoloration, change in gloss and colour, and / or the surface material being totally or partially delaminated

*****End of report*****



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS CSTC Standards Technical Services Co., Ltd.
Xiamen Branch Commercial General Laboratory

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China 361101
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编: 361101

t (86-592) 5765857 www.sgsgroup.com.cn
t (86-592) 5765857 sgs.china@sgs.com